

09/463042

430 Rec'd PCT/PTO 18 JAN 2000

UNITED STATES PATENT APPLICATION TRANSMITTAL FORM**BOX PCT****ASSISTANT COMMISSIONER FOR PATENTS****Washington, D.C. 20231**Docket No.: 360.6933USU**Attention: DO/EO/US**

Sir:

Transmitted herewith for filing is the patent application of

Applicant (s): Hanshan Dong; Peter Harlow Morton; Andrew
Bloyce and Thomas Bell

For: METHOD OF CASE HARDENING

International Application No.: PCT/GB98/02082

International Filing Date: 15 July 1998

ENTERING OF U.S. NATIONAL STAGE UNDER 35 U.S.C. §371

Transmitted herewith for filing are the following documents submitted under 37 C.F.R. §1.495(b) for the purpose of entering the national stage in the United States of America as an elected office. Enclosed are:

 Specification and Claims with Declaration;XXXXX Specification and Claims without Declaration;XXXXX 4 sheets of drawings;XXXXX Preliminary Amendment; An Assignment of the invention to: , including
\$40.00 recordation fee; The certified copy of a priority application;XXXXX Information Disclosure Statement with copies of patent(s) (Form -
PTO-1449); Verified Statement of Small Entity (Independent Inventor); Verified Statement of Small Entity (Small Business Concern);XXXXX Priority of application Serial No. 9715175.7, filed on 19 July
1997 in Great Britain; and PCT International Application No.
PCT/GB98/02082 filed on 15 July 1998 is claimed under 35
U.S.C. §119 and 35 U.S.C. §365;

097463042

420 Rec'd PCT/PTO 18 JAN 2000

XXXXX Cover page of published PCT Publication No. WO 99/04055 ;

XXXXX Copy of International Preliminary Examination dated 26 April 1999;

_____ Copy of PCT Demand Under Article 31; and

XXXXX Copy of International Search Report dated 27 October 1998.

_____ Copy of Written Opinion.

_____ Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371(c)(3)) are transmitted herewith.

The Filing Fee is calculated below.

CLAIMS AS FILED				
(1) For	(2) Number Filed	(3) Number Extra	(4) Rate	(5) Basic Fee \$670/\$760//\$840/ \$970/\$96
Total Claims	19 - 20 =	0	x \$18.00	\$0
Independent Claims	3 - 3 =	0	x \$78.00	\$0
Multiple Dependent Claim Fee		x \$260.00 = \$0.00		
TOTAL FILING FEE		\$840.00		
1/2 FILING FEE FOR SMALL ENTITY		\$10		

XXXXX Firm's check in the amount of \$ 840.00 to cover the filing fee;

XXXXX The Commissioner is hereby authorized to charge any additional fees under 37 C.F.R. 1.16 and 1.17 which may be required with this communication or during the entire pendency of the application, or credit any overpayment, to **Deposit Account No. 01-0467**. A duplicate copy of this Form is enclosed.


XXXXX Postcard.

09/463042

420 Rec'd PCT/PTO 18 JAN 2000

Address all future communications to: **Paul D. Greeley, Esq.**
Ohlandt, Greeley, Ruggiero & Perle, L.L.P.
One Landmark Square, 9th Floor
Stamford, Connecticut 06901-2682
U.S.A.

January 18, 2000
Date of Signature



Paul D. Greeley, Esq.
Attorney for Applicant(s)
Ohlandt, Greeley, Ruggiero & Perle, L.L.P.
Registration No. 31,019
Telephone: (203)327-4500
Telefax: (203) 327-6401

CERTIFICATE OF EXPRESS MAILING

I hereby certify that this paper or fee is being deposited with the United States Postal Service "Express Mail Post Office to Addressee" Certificate No. **EL466886290US**, service under 37 CFR §1.10 and is addressed to: Box PCT, Assistant Commissioner for Patents, Washington, D.C. 20231, Attention: DO/EO/US on January 18, 2000.

Joanne A. Romaniello
(Typed name of person mailing paper)



(Signature of person mailing paper)



Rec'd PCT/PTO

26 JUN 2002

09/463m47

Attny's Docket No. 360.6933USU**SMALL ENTITY DECLARATION**
[37 CFR 1.9(c-f)]

Each undersigned declares that:

- (1) ☐ the application attached hereto
(2) ☒ U.S. Application Serial No. _____ filed January 18, 2000
(3) ☐ U.S. Patent No. _____ issued _____

is entitled to the benefits of "small entity" status for paying reduced fees under 35 USC 41(a) and (b) to the Patent and Trademark Office by virtue of the following:

(4) ☒ Each undersigned declares that he/she qualifies as an independent inventor, or would qualify had he/she made the invention, as defined in 37 CFR 1.9(c).(5) ☐ The undersigned declares that he/she is an official empowered to act on behalf of the concern identified below; that this concern qualifies as a small business concern as defined in 37 CFR 1.9(d).(6) ☐ The undersigned declares the he/she is an official empowered to act on behalf on the organization identified below; that this organization qualifies as a nonprofit organization as defined in

- (a) ☐ 37 CFR 1.9(e)(1)
(b) ☐ 37 CFR 1.9(e)(2)
(c) ☐ 37 CFR 1.9(e)(3)
(d) ☐ 37 CFR 1.9(e)(4)

State law of _____

(7) Each person, concern or organization to which I/we have assigned, granted, conveyed or licensed, or am under an obligation under contract or law to assign, grant, convey, or license any rights in the invention is listed below:

- (a) ☐ no such person, concern or organization
(b) ☐ persons, concerns or organizations listed below

[a separate declaration is required from each named person, concern or organization having rights to this invention averring to their status as "small entities."]

Full Name The University of BirminghamAddress Edgbaston, Birmingham, B15 2TT, England☐ Individual ☒ Small Business Concern ☐ Nonprofit Organization

I/we acknowledge the duty to file, in this application or patent, notification of any change in status resulting in loss of entitlement of small entity status prior to paying, or at the time of paying, the earliest of the issue fee or any maintenance fee due after the date on which status as a small entity is no longer appropriate. (37 CFR 1.28(b))

I/we hereby declare all statements made herein of his/her own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application, any patent issued thereon, or any patent to which this declaration is directed.

- (8) Hanshan DONG HSDong 28 MARCH 2000
Typed Name of Inventor Signature Date
Peter Harlow MORTON PHMorton 28 MARCH 2000
Typed Name of Inventor Signature Date
(9) The University of Birmingham
Name of Small Business Concern or Nonprofit Organization
David JAMES ALLEN By David James Allen 28 MARCH 2000
Typed Name Signature Date
Registrar & Secretary
Title of Signatory

Attny's Docket No. 360.6933USU

SMALL ENTITY DECLARATION
[37 CFR 1.9(c-f)]

Each undersigned declares that:

- (1) ☐ the application attached hereto
(2) ☒ U.S. Application Serial No. _____ filed January 18, 2000
(3) ☐ U.S. Patent No. _____ Issued _____

is entitled to the benefits of "small entity" status for paying reduced fees under 35 USC 41(a) and (b) to the Patent and Trademark Office by virtue of the following:

(4) ☒ Each undersigned declares that he/she qualifies as an independent inventor, or would qualify had he/she made the invention, as defined in 37 CFR 1.9(c).

(5) ☐ The undersigned declares that he/she is an official empowered to act on behalf of the concern identified below; that this concern qualifies as a small business concern as defined in 37 CFR 1.9(d).

(6) ☐ The undersigned declares the he/she is an official empowered to act on behalf on the organization identified below; that this organization qualifies as a nonprofit organization as defined in

- (a) ☐ 37 CFR 1.9(e)(1)
(b) ☐ 37 CFR 1.9(e)(2)
(c) ☐ 37 CFR 1.9(e)(3)
(d) ☐ 37 CFR 1.9(e)(4)

State law of _____

(7) Each person, concern or organization to which I/we have assigned, granted, conveyed or licensed, or am under an obligation under contract or law to assign, grant, convey, or license any rights in the invention is listed below:

- (a) ☐ no such person, concern or organization
(b) ☐ persons, concerns or organizations listed below

[a separate declaration is required from each named person, concern or organization having rights to this invention averring to their status as "small entities."]

Full Name The University of Birmingham

Address Edgbaston, Birmingham, B15 2TT, England

☐ Individual ☒ Small Business Concern ☐ Nonprofit Organization

I/we acknowledge the duty to file, in this application or patent, notification of any change in status resulting in loss of entitlement of small entity status prior to paying, or at the time of paying, the earliest of the issue fee or any maintenance fee due after the date on which status as a small entity is no longer appropriate. (37 CFR 1.28(b))

I/we hereby declare all statements made herein of his/her own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application, any patent issued thereon, or any patent to which this declaration is directed.

(8) Andrew BLOYCE [Signature] 28 MARCH 2000
Typed Name of Inventor Signature Date
Thomas BELL [Signature] 28 MARCH 2000
Typed Name of Inventor Signature Date

(9) _____
Name of Small Business Concern or Nonprofit Organization

By _____
Typed Name Signature Date

Title of Signatory

09/463042

420 Rec'd PCT/PTO 18 JAN 2000

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Applicant: Dong et al.
Serial No.: Not Yet Assigned
For: METHOD OF CASE HARDENING
Filed: 18 January 2000
Examiner: Not Yet Assigned
Art Unit: Not Yet Assigned
Att'y Docket: 360.6933USU

Assistant Commissioner for Patents
Washington, D.C. 20231

PRELIMINARY AMENDMENT

Sir:

Applicant hereby submits this preliminary amendment simultaneously with the filing of this application, in accordance with 37 C.F.R. §§ 1.115 and 1.117.

IN THE CLAIMS

CLAIMS (USA)

1(amended). A method of case hardening an article formed of at least one material selected from the group consisting of titanium, zirconium, alloys of titanium, alloys of zirconium and alloys of titanium and zirconium, [titanium, zirconium or an alloy of titanium and/or zirconium,] said method comprising the steps of (a) heat-treating said[the] article [formed of titanium, zirconium or an alloy of titanium and/or zirconium] in an oxidising atmosphere containing both oxygen and nitrogen at a temperature in the range of 700 to 1000 °C so as to form an oxide layer on the article; and (b) further heat-treating the article in a vacuum or in a neutral or an inert atmosphere at a temperature in the range of 700 to 1000 °C so as to cause oxygen from the oxide layer to diffuse into the article.

2(amended). A method of case hardening an article formed of at least one material selected from the group consisting of titanium, zirconium, alloys of titanium, alloys of zirconium and alloys of titanium and zirconium, [titanium, zirconium or an alloy of titanium and/or zirconium,] said method comprising the steps of (a) heat-treating said [the] article [formed of titanium, zirconium or alloy of titanium and/or zirconium] in an oxidising atmosphere at a temperature in the range of 700 to 1000 °C so as to form an oxide layer on the article; and (b) further heat-treating the article in a vacuum or in a neutral or an inert atmosphere at a temperature in the range of 700 to 1000 °C so as to cause oxygen from the oxide layer to diffuse into the article whereby to produce a sigmoid-shaped hardness profile

3. A method as claimed in claim 2, wherein the oxidising atmosphere contains both oxygen and nitrogen.

4(amended). A method as claimed in claim 1[or 3], wherein the oxidising atmosphere in step (a) is air.

5(amended). A method as claimed in claim 1[any preceding claim], wherein the time for heat-treatment in step (a) is from 0.1 to 1 hour.

6(amended). A method as claimed in claim 1[any preceding claim], wherein the time for heat-treatment in step (a) is from 0.3 to 0.6 hour.

7(amended). A method as claimed in claim 1[any preceding claim], wherein the heat-treatment in step (a) is effected at atmospheric pressure.

8(amended). A method as claimed in claim 1[any preceding claim], wherein steps (a) and (b) are repeated at least once.

9(amended). A method as claimed in claim 1[any preceding claim], wherein the temperature in step (a) is 700 to 900 °C.

10. A method as claimed in claim 9, wherein the temperature in step (a) is 800 to 900 °C.

11(amended). A method as claimed in claim 1[any preceding claim], wherein the temperature in step (b) is 700 to 900 °C.

12. A method as claimed in claim 11, wherein the temperature in step (b) is 800 to 900°C.

13(amended). A method as claimed in claim 1[any preceding claim], wherein the heat treatment in step (b) is effected at a pressure of not more

than 1.3×10^{-2} Pa (1×10^{-4} Torr).

14. A method as claimed in claim 13, wherein the heat treatment in step (b) is effected at a pressure of about 1.3×10^{-4} Pa (1×10^{-6} Torr).

15(amended) A method as claimed in claim 1[any preceding claim], wherein the heat treatment in step (b) is effected for a time in the range of 10 to 30 hours.

16(amended). An article formed of a metal or alloy selected from the group consisting of titanium, zirconium, alloys of titanium and alloys of zirconium, said article having a hardened metallic case, strengthened by diffused oxygen; wherein the article has a sigmoid-shaped hardness profile across said hardened case.

17. An article as claimed in claim 16, wherein the depth of the hardened case is greater than 50 μm .

18. An article as claimed in claim 16, wherein the depth of the hardened case is in the range 200 to 500 μm .


19(amended). An article as claimed in claim 16[, 17 or 18], wherein a further layer of low-friction material is provided on top of the hardened case.

REMARKS

Applicant respectfully requests entry of the claim amendments.

Respectfully submitted,

Date: 18 January 2000



Paul D. Greeley
Reg. No. 31,019
Attorney for Applicant
Ohlandt, Greeley, Ruggiero & Perle, L.L.P.
One Landmark Square, 9th Floor
Stamford, CT 06901-2682
(203) 327-4500

1 420 Rec'd PCT/PTO 18 JAN 2000

METHOD OF CASE HARDENING

This invention relates to a method of case hardening and is more particularly concerned with a method of case hardening an article formed of titanium, zirconium or an alloy of titanium and/or zirconium.

In engineering applications, when a surface is subjected to a high contact load by another body, internal stresses are developed below the surface, the so-called Hertzian stresses. These stresses reach a maximum at a certain depth below the surface. Consequently, in order to withstand such stresses, it is necessary for a case-hardened layer to provide increased strength (and therefore hardness) down to at least that depth. At the same time, it is desirable to avoid excessive hardness at the surface itself as this could cause embrittlement. To reconcile these requirements, it is generally preferred to produce a hardness profile, in the direction normal to the surface, which has a sigmoid shape (see, for example, the OD curve in accompanying Fig 2), consisting of a region of relatively high hardness maintained to a certain depth below the surface before dropping more steeply and then gradually to the hardness of the untreated core material.

Both theoretical and experimental work has shown that significant improvements in the load-bearing capacity of a hard coating/sub structure system can be achieved provided that, in addition to a high interfacial adhesion strength, the substrate can firmly withstand the applied load without appreciable plastic deformation. This means that deep case surface engineering processes are beneficial for subsequent hard thin coatings on titanium alloys in view of their inherent low yield strengths and low elastic moduli. However, most titanium alloys, unlike ferrous materials, cannot be hardened to a great extent by conventional surface engineering techniques since there is no hardening reaction in titanium

2

alloys comparable to the martensite transformation in ferrous materials. Notwithstanding the fact that titanium alloys can be deeply hardened by electron beam surface alloying, it is still difficult in practice to achieve controlled reproducibility of composition in the alloyed surface layer. Oxidising titanium alloys at a high oxidation temperature for an extended period of time can also produce a deep hardened case. However, simple oxidation at higher temperatures (greater than 700°C) is prone to the formation of severe scaling, resulting in a crumbly surface oxide layer. The present invention relates to a method which avoids this by oxidation treatment at an elevated temperature effected for a relatively short period of time, followed by a subsequent heat treatment operation.

A method of surface hardening titanium by oxygen is disclosed by A. Takamura (Trans JIM, 1962, Vol. 3, pages 10-14). In one of the methods disclosed by Takamura, samples of commercial titanium are annealed, polished and degreased and are then oxidised in dry oxygen at 850°C for 1 or 1.5 hours. A thin oxide scale is formed on the surface of the samples. Then, the thus-oxidised samples are subjected to a diffusion treatment at 850°C for 24 hours in argon so as to cause oxygen to diffuse into the sample. In other methods disclosed by Takamura, the oxidised samples are diffusion treated first in argon and then in nitrogen or are diffusion treated in nitrogen. In no case, however, is the desirable sigmoid-shaped hardness profile achieved.

It is an object of the present invention to provide a process which is more capable of achieving the desirable sigmoid-shaped hardness profile than the last-mentioned publication.

According to a first aspect of the present invention, there is provided a method of case hardening an article formed of titanium, zirconium or an

3

alloy of titanium and/or zirconium, said method comprising the steps of (a) heat-treating the article formed of titanium, zirconium or alloy of titanium and/or zirconium in an oxidising atmosphere containing both oxygen and nitrogen at a temperature in the range of 700 to 1000°C so as to form an oxide layer on the article; and (b) further heat-treating the article in a vacuum or in a neutral or an inert atmosphere at a temperature in the range of 700 to 1000°C so as to cause oxygen from the oxide layer to diffuse into the article.

According to a second aspect of the present invention, there is provided a method of case hardening an article formed of titanium, zirconium or an alloy of titanium and/or zirconium, said method comprising the steps of (a) heat-treating the article formed of titanium, zirconium or alloy of titanium and/or zirconium in an oxidising atmosphere at a temperature in the range of 700 to 1000 °C so as to form an oxide layer on the article; and (b) further heat-treating the article in a vacuum or in a neutral or an inert atmosphere at a temperature in the range of 700 to 1000°C so as to cause oxygen from the oxide layer to diffuse into the article whereby to produce a sigmoid-shaped hardness profile.

The time for heat-treatment in step (a) is relatively short and depends, inter alia, upon the nature of the oxidising medium and the intended use of the article. Typically, the time may be, for example, from 0.1 to 1 hour, preferably 0.3 to 0.6 hour.

The heat-treatment in step (a) is conveniently effected at atmospheric pressure.

Steps (a) and (b) may be repeated at least once.

4

In the method according to said second aspect of the present invention, the oxidising atmosphere in step (a) preferably comprises oxygen as well as nitrogen, as this improves the adhesion of the predominantly oxide scale thus formed.

In the first and second aspects of the present invention, the oxidising atmosphere in step (a) is preferably air. The temperature in step (a) is preferably 700 to 900 °C, more preferably 800 to 900 °C, and most preferably about 850 °C.

The temperature in step (b) is preferably 700 to 900 °C, more preferably about 800 to 900 °C, and most preferably about 850 °C. It is most preferred to effect treatment step (b) in a vacuum, in which case the pressure is preferably not more than 1.3×10^{-2} Pa (1×10^{-4} Torr) Pa, and is conveniently about 1.3×10^{-4} Pa (1×10^{-6} Torr). The use of a vacuum is much preferred because it reduces the risk of unwanted contaminants being accidentally introduced into the surface of the article during step (b).

In particular, it is important to prevent gaseous oxygen from reaching the solid surface during step (b) where it may dissolve or react so as to cause excessive hardness and potential embrittlement. Where the heat treatment in step (b) is effected in an inert or neutral atmosphere, any non-oxidising and non-reducing atmosphere may be employed, such as argon or other inert gas, provided that it contains no or only a low partial pressure of oxygen.

The time required for the heat treatment in step (b) is typically in the range of 10 to 50 hours and may conveniently be about 20 to 30 hours.

It is within the scope of the present invention to follow the treatment steps

(a) and (b) with any of a variety of subsequent treatments or processes to reduce friction. In particular, it is within the scope of the present invention to follow the method of the present invention with the treatment method disclosed in our copending PCT Publication No. WO98/02595 for improving the tribological behaviour of a titanium or titanium alloy article.

Such process basically involves the gaseous oxidation of the article at a temperature in the range of 500 to 725 °C for 0.5 to 100 hours, the temperature and time being selected such as to produce an adherent and essentially pore-free surface compound layer containing at least 50 % by weight of oxides of titanium having a rutile structure and thickness of 0.2 to 2 μm on a solid solution - strengthened diffusion zone where the diffusing element is oxygen and the diffusion zone has a depth of 5 to 50 μm .

The present invention is applicable to commercially pure grades of titanium, titanium alloys (α , $\alpha + \beta$, or β alloys), commercially pure grades of zirconium, zirconium alloys and to alloys of zirconium and titanium.

Where the article is required to have good fatigue properties, it may be subjected to a mechanical surface treatment, such as shot peening, after heat treatment in order to restore the fatigue properties which may be reduced by the heat treatment operation.

According to a third aspect of the present invention, there is provided an article formed of a metal or alloy selected from titanium, zirconium, alloys of titanium and alloys of zirconium, said article having a hardened metallic case, strengthened by diffused oxygen; wherein the article has a sigmoid-shaped hardness profile across said hardened case.

Preferably, the depth of the hardened case is greater than 50 μm , and is

6

typically in the range 200 to 500 μm , but may be as great as 1 mm.

A further layer of low-friction material, for example, a nitride, diamond-like-carbon or an oxide layer as described in our co-pending PCT Publication No. WO98/02595, may be provided on top of the hardened case.

In the accompanying drawings:-

Fig 1 is an SEM micrograph showing the overall microstructure of a sample of an oxygen-diffused (OD) Ti6Al4V material treated in accordance with the method of the present invention,

Fig 2 is a graph showing microhardness profiles for the OD Ti6Al4V material produced in accordance with the present invention and for other surface-treated articles formed of the same material (Ti6Al4V),

Fig 3 is a graph showing the effect of OD treatment and OD plus shot peening (OD + SP) on the fatigue properties of Ti6Al4V,

Fig. 4 is a graph showing microhardness profiles for OD C.P titanium material, produced in accordance with the present invention,

Fig. 5 is a graph showing a microhardness profile for OD Timet551 produced in accordance with the present invention, and

Fig. 6 is a graph showing a microhardness profile for OD Timet10-2-3 material, produced in accordance with the present invention.

Samples of Ti6Al4V in the form of cylindrical coupons of 5 mm thickness, cut from a 25 mm diameter bar were used. The samples were then thoroughly cleaned and subsequently thermally oxidised at 850 °C for 30 minutes in air in a muffle furnace. After being allowed to cool, the samples were subjected to a further heat treatment operation at 850 °C for 20 hours in a vacuum furnace (about 1.3×10^{-4} Pa = about 10^{-6} Torr). Alternatively, the steps of (a) thermal oxidation and (b) further heat

treatment can be carried out in a single vacuum furnace, step (a) being effected in air and step (b) being effected at 1.3×10^{-4} Pa after evacuation of the air.

It was noted that, after thermal oxidation at 850 °C for 30 minutes, the samples had a dark brown appearance. However, this changed to silver following the further heat treatment operation. The metallography of the oxygen-diffused treated sample is shown in Fig 1. A hardened layer was produced which was which was estimated from the transition in morphology to have a depth of about 300 μm and appeared (from the different etching effects) to consist of two sub-layers, the first sub-layer having a depth of about 80 μm and the second sub-layer, lying under the first sub-layer, having a depth of about 220 μm .

A typical microhardness profile for the above-treated samples is illustrated in Fig 2 where, for comparison purposes, microhardness profiles are also given for samples of the same Ti6Al4V material treated by one of three processes, namely oxidation at 850 °C for 30 minutes, oxidation at 850°C for 20.5 hours and plasma nitriding at 850°C for 20 hours in an atmosphere of 25% N₂ and 75% H₂. It is notable that the OD material treated in accordance with the present invention showed the desired sigmoid hardness profile with a more pronounced hardening effect in terms of higher hardness and deep-hardened zone than the thermally oxidised material with the same thermal cycle (850 °C/20.5 hours). The microhardness profile for the OD material in accordance with the present invention is in good agreement with the observed microstructural features illustrated in Fig 1.

As can be seen from Fig 2, the OD samples produced in accordance with the present invention had a high hardness (greater than 700 HV_{0.05}) in the

first 80 μm and a total hardened layer of about 300 μm in depth.

As can be seen from Fig 3, OD treatment in accordance with the present invention reduces the fatigue properties of Ti6Al4V. However, the reduction in the fatigue limit was totally restored and slightly elevated by about 30 MPa over the untreated material by shot peening. In this particular case, the shot peening was effected using C glass shot with an Almen density of 0.15-0.029N.

As noted above, the samples treated in accordance with the present invention possessed a significantly greater depth of hardening effect than a direct oxidation treatment at the same temperature and for the same total time (850 °C/20.5 hours). This means that the treatment in accordance with the present invention not only avoids the formation of an undesirable scale, which always occurs as a result of oxidation treatment at high temperature, but also confers a greater case hardening effect. This phenomenon at first seems difficult to understand since, in both instances, a high oxygen potential exists at the air/oxide interface for the oxidation treatment or at the oxide/Ti interface for the treatment in accordance with the present invention. It is known that oxidation of titanium is controlled by oxygen diffusion in the diffusion zone rather than in the oxide, since the diffusion coefficient for oxygen in TiO_2 is about 50 times that in $\alpha\text{-Ti}$ at the same temperature. Therefore, there is no reason to relate to the difference in the hardening effect between the process of the present invention conducted at 850 °C for a total time of 20.5 hours and a simple oxidation treatment effected at 850 °C for 20.5 hours, to the diffusion resistance of oxygen passing through the oxide layer.

Without prejudice to the present invention, it is theorised that the above phenomenon is caused by the retarding effect of nitrogen (from the air) on

the diffusion of oxygen. During prolonged treatment in air, a build-up of nitrogen atoms may occur at the oxide/metal interface (see A.M. Chaze et al, Journal of Less-Common Metals, 124 (1986) pages 73 to 84) and may act as a block on the inward diffusion of oxygen. In the above described process according to the present invention, no further nitrogen is admitted during vacuum treatment and the blocking effect is therefore much reduced.

The examples quoted above for the alloy Ti-6Al-4V, have been case hardened using process parameters that have substantially been optimised for that alloy. In order to demonstrate that the process is equally applicable to other alloys of titanium, a limited number of samples of C.P titanium, Timet551 and Timet10-2-3 have also been treated. The following examples are for demonstration only and do not necessarily represent an optimised process.

Samples of C.P titanium in the form of rectangular blocks of 20x10x10mm, cut from a 10mm thick sheet, were used. The samples were degreased and then thermally oxidised in air at 850 °C for 20-30 minutes. After cooling, the samples were subjected to a further heat treatment operation at 850 °C for 22 hours in a vacuum furnace (about 1×10^{-6} Torr = about 1.3×10^{-4} Pa).

Samples of Timet551 in the form of rectangular blocks of 30x10x10mm, cut from a 90mm diameter bar, were used. The samples were degreased and then thermally oxidised in air at 900 °C for 19 minutes. After cooling, the samples were subjected to a further heat treatment operation at 900 °C for 20 hours in a vacuum furnace (about 1×10^{-6} Torr = about 1.3×10^{-4} Pa).

Samples of Timet10-2-3 in the form of rectangular blocks of 30x10x10mm,

10

cut from a 260 mm diameter forged disc, were used. The samples were degreased and then thermally oxidised in air at 900 °C for 25 minutes. After cooling, the samples were subjected to a further heat treatment operation at 900 °C for 20 hours in a vacuum furnace (about 1×10^{-6} Torr = about 1.3×10^{-4} Pa).

It was noted that, after thermal oxidation, the C.P and Timet551 samples exhibited a grey appearance, whereas the Timet10-2-3 material exhibited a black appearance.

As can be seen from Figs 4 and 5, the C.P and Timet551 hardness profiles exhibit the same type of sigmoid shape as Fig. 2 (OD) but 20 μ m deeper penetration in the case of Timet551 (c.f. Fig. 2); the slightly lower hardness and deeper penetration being attributed to the 20 hour 900 °C diffusion step.

As can be seen from Fig. 6, the metastable β material has developed a much deeper hardening compared with the $\alpha + \beta$ titanium alloys. The deeper penetration of the oxygen can firstly be attributed to the higher diffusivity of oxygen in the β phase (see Z. Liu and Welsch, Metallurgical Trans. A, Vol. 19A, April 1988, pg1121-1125) and also to a much thicker oxide layer which developed during step (a), compared with the $\alpha + \beta$ titanium alloys.

In some alloys, the thermochemical treatment carried out in step (a) and/or step (b) of the case hardening process may alter the microstructure and mechanical properties of the core material. In such cases, a further heat treatment may be carried out after the case hardening process in order to restore or optimise the core properties.

It is important in the present invention that the scale formed during step (a) should remain adherent to the surface in order to provide the oxygen reservoir required for step (b). Depending on the alloy, the adhesion of the scale during step (a) can be affected not only by the time and temperature employed but also by the nature of the oxidising atmosphere and by the surface finish and geometrical shape of the surface treated. When titanium is oxidised at around 850°C, the scale formed is significantly more adherent if the oxidising atmosphere is air rather than pure oxygen, and a model has been proposed to explain this as an effect of the presence of nitrogen. Our experiments have confirmed the superiority of an air atmosphere over oxygen in this respect, and it is therefore not only more economical but also a technically preferred option to use air as the oxidising atmosphere in step (a). The surface finish applied to all samples here described was obtained by finishing on 1200 grade SiC paper and this generally gave good adhesion.

It is to be understood that the case hardening process here described results in a relatively deep case of hardened material which enables it to withstand the sub-surface Hertzian stresses developed by high contact loads. The resultant surface has therefore a high load-bearing capacity, but this does not, of itself, confer good wear resistance to the surface. In order to obtain a surface with low friction, which is resistant to scuffing and galling, it will be necessary to apply a further layer or coating to the case hardened surface, or other surface treatment. Coatings, which have successfully been applied to the case hardened surface, include plasma nitriding, a diamond-like carbon coating, and the coating produced by the process described in our copending PCT Publication WO98/02595.

CLAIMS

1. A method of case hardening an article formed of titanium, zirconium or an alloy of titanium and/or zirconium, said method comprising the steps of (a) heat-treating the article formed of titanium, zirconium or alloy of titanium and/or zirconium in an oxidising atmosphere containing both oxygen and nitrogen at a temperature in the range of 700 to 1000 °C so as to form an oxide layer on the article; and (b) further heat-treating the article in a vacuum or in a neutral or an inert atmosphere at a temperature in the range of 700 to 1000 °C so as to cause oxygen from the oxide layer to diffuse into the article.
2. A method of case hardening an article formed of titanium, zirconium or an alloy of titanium and/or zirconium, said method comprising the steps of (a) heat-treating the article formed of titanium, zirconium or alloy of titanium and/or zirconium in an oxidising atmosphere at a temperature in the range of 700 to 1000 °C so as to form an oxide layer on the article; and (b) further heat-treating the article in a vacuum or in a neutral or an inert atmosphere at a temperature in the range of 700 to 1000 °C so as to cause oxygen from the oxide layer to diffuse into the article whereby to produce a sigmoid-shaped hardness profile
3. A method as claimed in claim 2, wherein the oxidising atmosphere contains both oxygen and nitrogen.
4. A method as claimed in claim 1 or 3, wherein the oxidising atmosphere in step (a) is air.
5. A method as claimed in any preceding claim, wherein the time

13

for heat-treatment in step (a) is from 0.1 to 1 hour.

6. A method as claimed in any preceding claim, wherein the time for heat-treatment in step (a) is from 0.3 to 0.6 hour.

7. A method as claimed in any preceding claim, wherein the heat-treatment in step (a) is effected at atmospheric pressure.

8. A method as claimed in any preceding claim, wherein steps (a) and (b) are repeated at least once.

9. A method as claimed in any preceding claim, wherein the temperature in step (a) is 700 to 900 °C.

10. A method as claimed in claim 9, wherein the temperature in step (a) is 800 to 900 °C.

11. A method as claimed in any preceding claim, wherein the temperature in step (b) is 700 to 900 °C.

12. A method as claimed in claim 11, wherein the temperature in step (b) is 800 to 900°C.

13. A method as claimed in any preceding claim, wherein the heat treatment in step (b) is effected at a pressure of not more than 1.3×10^{-2} Pa (1×10^{-4} Torr).

14. A method as claimed in claim 13, wherein the heat treatment in step (b) is effected at a pressure of about 1.3×10^{-4} Pa (1×10^{-6} Torr).

15. A method as claimed in any preceding claim, wherein the heat

14

treatment in step (b) is effected for a time in the range of 10 to 30 hours.

16. An article formed of a metal or alloy selected from titanium, zirconium, alloys of titanium and alloys of zirconium, said article having a hardened metallic case, strengthened by diffused oxygen; wherein the article has a sigmoid-shaped hardness profile across said hardened case.
17. An article as claimed in claim 16, wherein the depth of the hardened case is greater than 50 μm .
18. An article as claimed in claim 16, wherein the depth of the hardened case is in the range 200 to 500 μm .
19. An article as claimed in claim 16, 17 or 18, wherein a further layer of low-friction material is provided on top of the hardened case.

ABSTRACT

A method of case hardening an article formed of titanium, zirconium or an alloy of titanium and/or zirconium is disclosed. First, the article is heat-treated in an oxidising atmosphere at a temperature in the range of 700 to 1000°C so as to form an oxide layer on the article. Then, the article is further heat-treated in a vacuum or in a neutral or inert atmosphere at a temperature in the range of 700 to 1000°C so as to cause oxygen from the oxide layer to diffuse into the article.



Figure 1




Figure 2




Figure 3

3/4




Figure 4




Figure 5

4/4




Figure 6



DECLARATION AND POWER OF ATTORNEY FOR PATENT APPLICATION

360.6933USU

Docket No. _____

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name.

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled:

Method of Case Hardening

the specification of which

(check one)

_____ is attached hereto.

X

was filed on 01/18/00 as Application Serial No. _____

and was amended on _____ (if applicable).

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose to the U.S. Patent and Trademark Office all information known to me to be material to the patentability of this application as defined in Title 37, Code of Federal Regulations, §1.56.

I hereby claim foreign priority benefits under Title 35, United States Code, §119 of any foreign application(s) for patent or inventor's certificate(s) listed below and have also identified below any foreign application(s) for patent or inventor's certificate(s) having a filing date before that of the application on which priority is claimed:

Prior Foreign Application(s)

Priority Claimed

9715175.7

Great Britain

19 July 1997

X Yes ___ No

(Number)

(Country)

(Day/Mon/Year Filed)

PCT/GB98/02082

PCT

15 July 1998

X Yes ___ No

(Number)

(Country)

(Day/Mon/Year Filed)

___ Yes ___ No

(Number)

(Country)

(Day/Mon/Year Filed)

I hereby claim the benefit under Title 35, United States Code, §120 of any United States application(s) listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States application in the manner provided by the first paragraph of Title 35, United States Code, §112, I acknowledge the duty to disclose material information as defined in Title 37, Code of Federal Regulations, §1.56(a) which occurred between the filing date of the prior application and the national or PCT international filing date of this application:

(Application Serial No.)

(Filing Date)

(Status)
(patent, pend., abandon.)

(Application Serial No.)

(Filing Date)

(Status)
(patent, pend., abandon.)

(Application Serial No.)

(Filing Date)

(Status)
(patent, pend., abandon.)

POWER OF ATTORNEY: As a named inventor, I hereby appoint the following attorney(s) and/or agent(s) to prosecute this application and transact all business in the Patent and Trademark Office connected therewith.

NAMES	REGISTRATION NUMBERS
Paul D. Greeley	<u>31,019</u>
John F. Ohlandt	<u>19,615</u>
Charles N.J. Ruggiero	<u>28,468</u>
David N. Koffsky	<u>19,905</u>

SEND CORRESPONDENCE TO: Paul D. Greeley, Esq. Ohlandt, Greeley, Ruggiero & Perle One Landmark Square Suite 903 Stamford, Connecticut 06901	DIRECT TELEPHONE CALLS TO: Paul D. Greeley, Esq. (203)327-4500
--	---

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

FULL NAME OF INVENTOR	LAST NAME DONG	FIRST NAME Hanshan	MIDDLE NAME
RESIDENCE & CITIZENSHIP	CITY Birmingham GBN	STATE OR COUNTRY Great Britain	CITIZENSHIP Chinese
POST OFFICE ADDRESS	P.O. ADDRESS 49 Griffin Close,	CITY & STATE Bristol Road South, Birmingham B31 2UY	ZIP CODE United Kingdom

Inventor's signature *H Dong* Date 28 MARCH 2000

FULL NAME OF INVENTOR	LAST NAME MORTON	FIRST NAME Peter	MIDDLE NAME
RESIDENCE & CITIZENSHIP	CITY Solihull GBN	STATE OR COUNTRY Great Britain	CITIZENSHIP British
POST OFFICE ADDRESS	P.O. ADDRESS 18 Barnbrook Road,	CITY & STATE Knowle, Solihull, B93 9PW	ZIP CODE United Kingdom

Inventor's signature *P Morton* Date 28 MARCH 2000

FULL NAME OF INVENTOR	LAST NAME BLOYCE	FIRST NAME Andrew	MIDDLE NAME
RESIDENCE & CITIZENSHIP	CITY Worcestershire	STATE OR COUNTRY Great Britain	CITIZENSHIP British GBN
POST OFFICE ADDRESS	P.O. ADDRESS 7 The Tyres, Bromsgrove, Worcestershire, B60 3QQ	CITY & STATE	ZIP CODE United Kingdom

Inventor's signature *A Bloyce* Date 28 MARCH 2000

POWER OF ATTORNEY: As a named inventor, I hereby appoint the following attorney(s) and/or agent(s) to prosecute this application and transact all business in the Patent and Trademark Office connected therewith.

NAMES	REGISTRATION NUMBERS
Paul D. Greeley	31,019
John F. Ohlandt	19,615
Charles N.J. Ruggiero	28,468
David N. Koffsky	19,905

SEND CORRESPONDENCE TO:	DIRECT TELEPHONE CALLS TO:
Paul D. Greeley, Esq. Ohlandt, Greeley, Ruggiero & Perle One Landmark Square Suite 903 Stamford, Connecticut 06901	Paul D. Greeley, Esq. (203)327-4500

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

4-00

FULL NAME OF INVENTOR	LAST NAME BELL	FIRST NAME Thomas	MIDDLE NAME
RESIDENCE & CITIZENSHIP	CITY Merseyside <i>GBN</i>	STATE OR COUNTRY Great Britain	CITIZENSHIP British
POST OFFICE ADDRESS	P.O. ADDRESS St. Mawes, 1 Mariners Road, Blundellsands, Merseyside	CITY & STATE	ZIP CODE L23 6SX United Kingdom

Inventor's signature *T. Bell* Date 28 MAR 2000


FULL NAME OF INVENTOR	LAST NAME	FIRST NAME	MIDDLE NAME
RESIDENCE & CITIZENSHIP	CITY	STATE OR COUNTRY	CITIZENSHIP
POST OFFICE ADDRESS	P.O. ADDRESS	CITY & STATE	ZIP CODE

Inventor's signature _____ Date _____

FULL NAME OF INVENTOR	LAST NAME	FIRST NAME	MIDDLE NAME
RESIDENCE & CITIZENSHIP	CITY	STATE OR COUNTRY	CITIZENSHIP
POST OFFICE ADDRESS	P.O. ADDRESS	CITY & STATE	ZIP CODE

Inventor's signature _____ Date _____

United States Patent & Trademark Office
Office of Initial Patent Examination -- Scanning Division



Application deficiencies found during scanning:

☐ Page(s) _____ of _____ were not present
for scanning. (Document title)

☐ Page(s) _____ of _____ were not present
for scanning. (Document title)

☒ Scanned copy is best available. *Some drawings are too dark.*